

DuPont™ Pyralux® AP

All-Polyimide Double-Sided Copper-Clad Laminate

Flexible Circuit Materials

Product Description

DuPont™ Pyralux® AP is a Double-sided Copper-clad Laminate featuring an adhesive-less, all-polyimide dielectric layer. This material is ideal for multilayer flex and rigid-flex applications that required advanced performance, including low loss properties for excellent signal integrity and thermal resistance for high reliability. Available in a range of conductor and dielectric thicknesses, Pyralux® AP clads provide designers and fabricators outstanding options for fabricating high performance circuits.

Key Features and Benefits

- Low loss all-polyimide dielectric for superior signal integrity
- Excellent bond strength affords high reliability
- High thermal resistance to facilitate processing
- Balanced and unbalanced constructions available
- Certified to IPC-4204/11
- UL 94 V-0, UL File E124294
- RoHS Compliant

Packaging

Pyralux® AP Double-side Clad is supplied in sheet form, with standard dimensions of 24 x 36 in (610 x 914 mm), 24 x 18 in (610 x 457 mm), and 12 x 18 in (305 x 457 mm).

Storage and Warranty

DuPont™ Pyralux® AP Double-side Clad should be stored in original packaging at temperatures of 4 - 29 °C (40 - 85 °F) and below 70% relative humidity. The product should not be refrigerated or frozen and should be kept dry, clean, and well protected. Subject to compliance with the foregoing handling and storage recommendations, DuPont's warranties shall remain in effect for the period provided in the DuPont Standard Conditions of Sale

Safe Handling

Prior to handling, DuPont recommends referencing the Pyralux® Safe Handling Guide available at pyralux.dupont.com.

Table 1 - Pyralux® AP Construction Options

Laminate Component			
Copper Foil Thickness, μm (oz/ft ²)	6 (0.17)	18 (0.5)	105 (3.0)
	9 (0.25)	35 (1.0)	140 (4.0)
	12 (0.33)	70 (2.0)	
Copper Foil Type	RA, ED, and Double-treated RA		
Dielectric Thickness, μm (mil)	12 (0.5)	50 (2.0)	125 (5.0)
	25 (1.0)	75 (3.0)	150 (6.0)

Table 2 - Standard Pyralux® AP Offerings

Product Code*	Copper Thickness μm (oz/ft ²)	Dielectric Thickness μm (mil)
AP8515R	18 (0.5)	25 (1.0)
AP9111R	35 (1.0)	25 (1.0)
AP9121R	35 (1.0)	50 (2.0)
AP9131R	35 (1.0)	75 (3.0)
AP9141R	35 (1.0)	100 (4.0)
AP9151R	35 (1.0)	125 (5.0)
AP9161R	35 (1.0)	150 (6.0)

*At the end of the product code, "R" designates rolled-annealed copper (e.g., AP9111R), "E" designates electro-deposited copper (e.g., AP9111E), and "D" designates double-treated rolled-annealed copper (e.g., AP9111D).

Pyralux® AP Double-Side Clad Construction Selection

A variety of Pyralux® AP Double-side Clad constructions, both balanced and unbalanced, are commercially available. For help beyond the standard offerings in Table 1, please use the Laminate Product Selector at pyralux.dupont.com to identify the appropriate product code for your copper-clad laminate solution.



Processing

DuPont™ Pyralux® AP Double-side Clad are fully compatible with all conventional flexible circuit fabrication processes, including oxide treatment and wet chemical plated-through-hole de-smearing. Fabricated circuits can be cover coated and laminated together to form multilayers or bonded to heat sinks using polyimide, acrylic, or epoxy adhesives.

DuPont™ Pyralux® AP

All-Polyimide Double-Sided Copper-Clad Laminate
Flexible Circuit Materials

Product Performance

Table 3 - DuPont™ Pyralux® AP Double-sided Copper-clad Laminate Properties

Property	AP9121 Typical Value	Test Method
Dielectric Constant (Dk) 1 MHz 10 GHz	3.4 3.2	IPC-TM-650 2.5.5.3 ASTM D2520
Loss Tangent (Df) 1 MHz 10 GHz	0.002 0.003	IPC-TM-650 2.5.5.3 ASTM D2520
Peel Strength (Adhesion to Copper) As Received, N/mm (lb/in) After Solder, N/mm (lb/in)	1.4 (8) 1.4 (8)	IPC-TM-650 2.4.9
Dimensional Stability (MD/TD) After Etching, % After Thermal, %	-0.04 to -0.08% -0.04 to -0.08%	IPC-TM-650 2.2.4
Coefficient of Thermal Expansion XY-Axis, ppm/°C	Below Tg 25 / Above Tg 30	IPC-TM-650 2.4.41
Solder Float, 288 °C for 10 s	Pass	IPC-TM-650 2.4.13
Moisture Absorption, %	0.8	IPC-TM-650 2.6.2
Moisture & Insulation Resistance, Ω	> 10 ¹¹	IPC-TM-650 2.6.3.2
Dielectric Strength, V/μm	200	ASTM D149
Volume Resistivity, Ω · cm	> 10 ¹⁷	IPC-TM-650 2.5.17
Surface Resistance, Ω	> 10 ¹⁶	IPC-TM-650 2.5.17
Tensile Modulus, GPa	4.8	IPC-TM-650 2.4.19
Tensile Strength, MPa	345	IPC-TM-650 2.4.19
Elongation, %	50	IPC-TM-650 2.4.19
Flexural Endurance, cycles	6,000	IPC-TM-650 2.4.3
Glass Transition Temperature (Tg), °C	220	DuPont Method, TMA

Data within this table are typical values for the listed product. Performance can vary depending on construction and processing.

Quality and Traceability

DuPont™ Pyralux® AP Double-side Clad is manufactured under a certified ISO9001:2015 Quality Management System facility. Complete material and manufacturing records, which include archive samples of finished product, are maintained by DuPont. Each manufactured lot is identified for reference traceability. The packaging label serves as the primary tracking mechanism in the event of customer inquiry and includes the product name, batch number, size, and quantity.



For more information on DuPont™ AP Double-side Clad or other DuPont products, please visit our website.

pyralux.dupont.com

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions, DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5 and "DuPont Policy Regarding Medical Applications" H-50103-5.

DuPont™, the DuPont Oval Logo, and all products, unless otherwise noted, denoted with ™, ® or ® are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. Copyright © 2025 DuPont de Nemours Inc. All rights reserved.

EI-10124 (2/25)